

# EMACO<sup>®</sup> NANOCRETE FC

Cementitious polymer modified thin layer fairing mortar

## DESCRIPTION

**Emaco Nanocrete FC** is a concrete-grey, ready-to-use mortar based on hydraulic binders, high grade quartz sands and modified with synthetic polymers. It contains no chlorides or other salts that might cause corrosion or blooming.

## RECOMMENDED FOR

**Emaco Nanocrete FC** is especially suitable for levelling uneven surfaces, filling honeycombs and pin holes.

It can be used as a topping (render) of up to 3mm thick to face up masonry.

**Emaco Nanocrete FC** is an ideal substrate for coatings. It is also used for laying ceramic and concrete tiles, and as a thin bed mortar for the placement of lightweight blocks, insulation boards and hollow masonry units (HMU).

**Emaco Nanocrete FC** is ideal for thin resurfacing of damaged concrete surfaces, such as in rain damaged slabs and for use in non-moving crack repairs.

## FEATURES AND BENEFITS

- Economical
- For thin layer patching
- As base layer for coatings, tiles and panels
- Quick and easy to apply
- Excellent bonding
- Very durable
- Shrinkage compensated
- Feather edging possible
- Water and weatherproof
- High early strength

Well mixed **Emaco Nanocrete FC** yields a plastic, thixotropic compound, that is easily applied. It is non-sagging on vertical surfaces or overhead. The very fine polymers ensure excellent anchorage and adhesion to the substrate and improves the water retention considerably, thus preventing the formation of cracks.

After curing, **Emaco Nanocrete FC** is waterproof and resistant to weather and frost. Besides high compressive strength, it offers excellent bonding and tensile strengths.

## ESTIMATING DATA

A 20kg bag of **Emaco Nanocrete FC** mixed with 4 litres of water yields 12 litres (0.012m<sup>3</sup>), therefore material requirement is 5kg/m<sup>2</sup> @ 3mm thickness.

## PERFORMANCE DATA

	<b>28 days</b>
Compressive strength	40 MPa
Flexural strength	7.0 MPa
E-Modulus	12.0 GPa
Bond (to substrate)	> 2.5 MPa
Co-efficient of thermal expansion (ASTM C531)	13 x 10 <sup>-6</sup> m/m/°C

## SPECIFICATIONS

Supply form	powder
Water added per bag (20kg)	up to 4 litres
Colour	grey
Density (mixed)	2.0 kg/litre
Storage temperature	moderate
Effect of humidity	same as cement
Applic. temperature	not below 7°C
Physiological effects	same as cement
Toxicity	non-toxic
VOC Content: 7g/L	Test method: SCAQMD: 304-91

## TEST REPORTS

Test reports are available upon request.

## APPLICATION

### Substrate Condition

Surfaces to which **Emaco Nanocrete FC** mixtures are to be applied, should be clean, sound and free of dust and loose particles.

Cement laitance, oil, grease, mould release oil or curing compound must be removed from concrete surfaces by using wire brush, bush hammer, scabber, gritblasting or other means. Ensure that steel rebars are also clean from grease, oil or rust. When repairing spalled or deteriorated concrete, ensure that the concrete has been cut back to sound material.

Steel surfaces should be degreased with a suitable solvent or treated by gritblasting. In many cases where corrosion is absent, wire brushing to a clean bright surface is sufficient.

All absorbent surfaces to be treated with **Emaco Nanocrete FC** mortars must be thoroughly dampened to saturate all pores. During application, the temperature of the substrate should not be below 7°C.

To avoid too high surface temperatures it is advised to shade areas for the period of application.

Grooves more than 3mm deep should be prefilled with **Emaco Nanocrete R2**.

### Mixing

Pour water into a suitable pail and add **Emaco Nanocrete FC** whilst mixing continuously until a homogeneous, lump-free mix is obtained.

The amount of water to be added is highly dependent on ambient temperature and relative humidity. In hot and dry climates, slightly higher amounts of water may be necessary, the contrary in cold and humid climates.

Use a low speed stirrer with a suitable mixing paddle to entrap as little air as possible.

Do not mix **Emaco Nanocrete FC** with additional cement, sand or aggregate.

### Priming

Is not required.



The Chemical Company

# EMACO<sup>®</sup> NANOCRETE FC

## Method of use

Apply the well-mixed **Emaco Nanocrete FC** without delay to the prepared damp surface with a spatula or trowel; thin layers may be applied with a brush. A minimum temperature of 7°C is essential. Layers up to a maximum of 3mm per coating can be applied.

If **Emaco Nanocrete FC** is used as an adhesive, either spot or full surface bonding can be used. Bring the material being bonded into the correct position and press down firmly.

Depending on the finish desired, treat the surface of **Emaco Nanocrete FC** after it starts to set with a foam or sponge trowel.

## Tools:

Mixing : low speed drill  
Applic. : spatula, trowel or brush  
Finish : wood or steel trowel to obtain very smooth surface, but avoiding a layer of laitance, it is best to smooth with foam or sponge trowel.

## POT LIFE

The working time of **Emaco Nanocrete FC** depends on the temperature:-

at 20°C, about 50 minutes  
at 30°C, about 25 minutes

If longer working time is required, a small amount of water can be added (maximum 2%) before the mix starts to set, e.g. by wetting the trowel with water.

## CURING

All cementitious mortars and concrete have to be protected against too rapid surface evaporation immediately after placement. Freshly applied patches should therefore not be exposed to direct sunlight, wind or rain. Covering with wet hessian or plastic sheet for a period of 24 hours is recommended.

## CLEANING

**Emaco Nanocrete FC** is a cementitious product. Tools should be cleaned with water before material hardens.

As **Emaco Nanocrete FC** is extremely sticky, it is advisable to wear rubber gloves when handling it.

## SHELF LIFE

**Emaco Nanocrete FC** can be stored in tightly sealed original bags for 6 months, if kept dry and at moderate temperature.

## PACKAGING

**Emaco Nanocrete FC** is available in 20kg bags.

## PRECAUTIONS

**Emaco Nanocrete FC** is not toxic, but as with other products containing Portland cement it has an alkaline nature and thus can be irritating to skin and eyes. Wear simple dust masks and gloves when handling.

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Construction Chemicals **Material Safety Data Sheet (MSDS)** from our office or our website.

AENcreteFC/2/0809

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF Construction Chemicals** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. **BASF Construction Chemicals data sheets are updated on a regular basis and it is the user's responsibility to obtain the most recent issue.**

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF Construction Chemicals**, are responsible for carrying out procedures appropriate to a specific application.

**BASF Construction Chemicals Australia Pty Ltd** Incorporated in NSW A.B.N. 46 000 450 288

**Sydney-Head Office:** 11 Stanton Road Seven Hills, NSW 2147 Australia Ph. (02) 8811 4200

**Newcastle:** (02) 4961 3819 **Brisbane:** (07) 3633 9900 **Townsville:** (07) 4774 7344 **Melbourne:** (03) 9549 0300

**Adelaide:** (08) 8139 7500 **Perth:** (08) 9366 2600 **Kalgoorlie:** 0417 772 355

**BASF Construction Chemicals New Zealand Head Office:** 45 William Pickering Drive, Albany, Auckland Ph: (09) 414 7233

**BASF Websites:** [www.basf-cc.com.au](http://www.basf-cc.com.au) [www.basf-cc.co.nz](http://www.basf-cc.co.nz) [www.basf-ugc.com](http://www.basf-ugc.com)