

MasterFlow® 928 (Formerly known as EMACO® S55)

Cementitious high strength non-shrink precision grout

Description of Product

MasterFlow® 928, is cement based one component, self compacting non-shrink grout.

- foundations,
- Fixing of the steel columns on the RC foundations,
- Filling of the voids in the jacketing applications.

Complies with EN 1504-6 and EN 1504-3/R4 ASTM C1107 Type B and Type C


Features and Benefits

Fields of Application

- Construction of shear wall caps and column caps,
- Fixing of pre-cast concrete elements,
- Fixing of the turbines on the foundations,
- Fixing of the generators, compressors and pumps on the foundations,
- Fixing of the industrial machines on the

- Mixed with only water and can be applied easily.
- High compressive strength.
- High fluid consistency.
- Free of bleeding.
- Resistant to water and weather conditions.
- Perfect bonding to the concrete and steel.
- Non-shrink.

Technical Data

Product Chemistry	Mineral Fillers and Cement	
Color	Grey	
Compressive Strength TS EN 196 (1 day) (7 days) (28 days)	> 30 N/mm ² > 50 N/mm ² > 60 N/mm ²	
Flexural Strength TS EN 196 (28 days)	8 N/mm ²	MK
Bonding Strength TS EN 1542 (28 days) to concrete to steel	> 2.0 N/mm ² > 2.0 N/mm ²	
Elasticity Modulus TS EN 13412 (28 days)	> 20,000 N/mm ²	
Capillary Water Absorption (TS EN 13057)	≤ 0.5 kg.m-2.hour-0.5	
Application Thickness	Min 10 mm Max 40 mm	
Application Temperature	+5°C - +30°C	
Service Temperature	-20°C - +400°C	
Pot Life	45 minutes	
Open Time to Pedestrian Traffic	24 hours	
Fully Cured at 20°C	28 days	

Typical values are obtained from the test results of 4x4x16 mortar prism in 23°C and 50% relative humidity conditions. High temperatures shortens the curing and working time, lower temperatures extends the durations



The Chemical Company

MasterFlow® 928 (Formerly known as EMACO® S55)

Application Procedure

Preparation of Substrate

The concrete should be free of frost, curing membranes, waterproofing treatments, oil stains, laitance, friable material and dust. The concrete surfaces should be chipped and if there is a water leakage it must be drained or properly plugged. Base plate, rods and bolts should be free of oil stains, grease and dust. Enough number of holes should be opened on the base plate for air drain. Machine should be assembled and balanced before grouting. The concrete surfaces should be saturated with water at least 6 hours before the grouting.

Formwork Preparation

The form material should be waterproof and resistant to hydrostatic forces of the grout. Formwork installation should be done against the possible leakage of the cement paste. An opening should be designed in the formwork with a width of 5 cm at minimum for pouring the grout. For providing a constant pressure for easy compacting of the grout the forms should be as high as possible in the pouring side. In grouting of huge base plates, special pipe and pump systems can be used or grout can be prepared with 5% extra water. For preventing the pressure releases, the forms should be placed without any tolerances and gaps between the concrete and form material.

Mixing

Add enough water into a clean mixing bucket by using a proper water gauge. Add the powder into the bucket slowly and continuously. Mix the fresh mortar with a proper electrical mixer (300-600 rpm) for 4 minutes until having a

homogenous consistency. Let the mortar have rest for 4 minutes and re-mix for 30 seconds.

Mixing Ratio

MasterFlow® 928	1 kg powder	25 kg bag
Water Quantity	< 0.16 litre	< 4.00 litre
Mixed Density	~2.20 kg/litre	

Application Method

In the case of operating neighbour machines, a glass of water should be put on the grouting base and the vibrations caused by the environment can be observed. If needed, surrounding machines should be switched off until (10-12 hours in 20°C) the grout sets.

MasterFlow® 928 should be poured directly into the formwork or it should be pumped under pressure. Application thickness should be 1-4 cm. For preventing the possible air gaps in the formwork, pour the grout from single opening and let the air draining. Use a steel hook for placing the grout under the plates and do not use vibrator. For thicker applications second layer of the mortar should be applied in same way or consult to the **BASF Yapı Kimyasalları** Technical Service.

Coverage

19.00 kg/m² for obtaining 1 cm thick layer.

Watch Points

- During the application the substrate and ambient temperature should be between 5-30°C.
- Open areas should be protected from the rain, wind, etc. aggressive weather conditions during the first 24-48 hours after finishing repair.



The Chemical Company

MasterFlow[®] 928 (Formerly known as EMACO[®] S55)

- Cement based materials' pot life and curing times vary depending on the relative humidity, substrate and ambient temperature. Reaction gets slow in low temperatures and it causes to extension on pot life and working time. On the other hand high temperatures speed up the reaction, which results to short pot life and working time. For full curing of material, both the substrate and ambient temperature shouldn't be under allowed application temperature.
- Do not use **MasterFlow[®] 928** in case of contacting to liquids with a PH under 5.5.
- Do not use vibrator for placing the mortar.
- In low temperatures (5°C-10°C) the following precautions should be taken;
The product should be stored in warm conditions,
Hot water (30°C-50°C) should be used for mixing,
Grouting area should be heated and protected from cold.
- In high temperatures (25°C-30°C) the following precautions should be taken;
The product should be stored in cool conditions,
Cold water (0°C-10°C) and ice should be used for mixing,

Cleaning of Tools

After the application all tools should be cleaned with water. **MasterFlow[®] 928** can be cleaned with only mechanical abrasion after hardening.

Packaging

25 kg bag

Storage

Store in original container in cool (+5°C - +25°C) and dry indoor conditions.

Shelf Life

12 months under proper storage conditions after production date.

Health and Safety Precautions

It is dangerous to get close to the store areas with fire. The store must be well ventilated.

Work clothes, protective gloves, glasses and mask defined in Labour Laws must be used during the application. Avoid from material to contact with skin and eyes. In case of contacting wash your skin with water and go to doctor immediately.

Don't bring any food and drink to the application area. Store the material away from the children. For further information Material Safety Data Sheets should be read.



The Chemical Company

MasterFlow[®] 928 (Formerly known as EMACO[®] S55)

The information given here is true, represents our best knowledge and is based not only on laboratory work but also on field experience. However, because of numerous factors affecting results, we offer this information without guarantee and no patent liability is assumed. For additional information or questions, please contact your local representative.

BASF Central Asia
Rayimbek ave., 211A Almaty/Kazakhstan
Phone +7 727 2790013
Fax +7 727 2333282
Visit us: www.master-builders-solutions.basf.kz